

PLASKLEEN-A

PRODUCT DATA SHEET

SELECTION & SPECIFICATION DATA

Generic Type

Cleaning solution

Description

Plaskleen-A is a cleaning solution used in conjunction with Plasite 3070, 3070 L and 3076. When the surface to be coated has previously been in sulfuric acid service, Plaskleen-A must be used.

One gallon of Plaskleen-A Concentrate to 10 gallons of tap water (total of 11 gallons of solution) will cover approximately 270 ft2 (25.08 sq2) per each gallon of mixed solution (coverage may vary depending upon condition of steel).

Coverage Rate

Note: Coverage information has been obtained through field experience. Plaskleen-A solution shall be applied after the steam cleaning of prebaking procedures and prior to final blast.

MIXING & THINNING

- 1. Store Plaskleen-A Concentrate at room temperature.
- 2. Before diluting Plaskleen-A Concentrate, check for the following:

Mix or shake Concentrate thoroughly making sure any solid residue is in solution.

Mixing

If Concentrate has been frozen, or is very cold, a crystalline mass will form. Allow Concentrate to reach room temperature and mix or shake into solution.

3. After Concentrate is in solution, while mixing add Concentrate (at a ratio of 10 gallons tap water to 1 gallon Plaskleen-A Concentrate) slowly to tap water and mix the diluted solution at least 5 minutes.

Ratio | One gallon of Plaskleen-A Concentrate to 10 gallons of tap water (total of 11 gallons of solution)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Airless Spray

Plaskleen-A solution is applied with airless spray equipment with a minimum of 1800 psi liquid pressure. The objective is to thoroughly wet out and completely saturate all exposed surfaces.

PACKAGING, HANDLING & STORAGE

Packaging | 1 Gallon & 5 Gallon Units

Shipping Weight | 1 Gallon Unit - 10 lbs (4.5 kg) (Approximate) | 5 Gallon Unit - 50 lbs (22.7 kg)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.