

SELECTION & SPECIFICATION DATA

Generic Type	Modified Epoxy Coating
Description	Carbomastic 18 NT is a heavy duty, high build coating for the protection of steel in corrosive environments. It is an excellent replacement lining for coal-tar epoxies where coal-tar is not allowed.
Features	<ul style="list-style-type: none"> • Excellent immersion performance in both fresh and sea water • Suitable as a rust preventive coating in ballast tanks and hull applications • Ideal for sub-sea installations, jackets and other areas prone to condensation • Can be applied as low as 5°C (40°F) • Good flexibility • Very good abrasion resistance • VOC compliant
Color	Gray (0700) and Buff (0200)
Finish	Semi-Gloss
Primer	Self-priming
Dry Film Thickness	8 - 10 mils (203 - 254 microns) per coat 5-20 mils depending on application. Typically 8-10 mils per coat.
Solids Content	By Volume 80% +/- 2%
Theoretical Coverage Rates	
Theoretical Coverage Rate	1283 ft²/gal at 1.0 mils (31.5 m²/l at 25 microns) 160 ft²/gal at 8.0 mils (3.9 m²/l at 200 microns) 128 ft²/gal at 10.0 mils (3.1 m²/l at 250 microns) Allow for loss in mixing and application.
VOC Values	As Supplied 1.34 lbs./gal (160 g/l) These are nominal values.
Dry Temp. Resistance	Continuous: 250°F (121°C) Non-Continuous: 300°F (149°C)
Limitations	Epoxies lose gloss, discolor and eventually chalk in sunlight exposure. Not recommended for immersion in aromatic or ketone solvents or strong oxidizing acids.
Thinner & Cleaner	<ul style="list-style-type: none"> • Thinner: Thinner #10 • Cleaner: Thinner #2
Topcoats	Not normally topcoated.

SUBSTRATES & SURFACE PREPARATION

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Carboline Surface Cleaner 3 is recommended.
----------------	---

SUBSTRATES & SURFACE PREPARATION

Steel | Immersion: (SSPC-SP10) with a 2-3 mil surface profile.
Non-Immersion: (SSPC-SP2) minimum is acceptable.
Surface Profile: 2.0-3.0 mils (50-75 micron)

Concrete or CMU | Concrete must be cured 28 days at 20°C and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing.

PERFORMANCE DATA

Test Method	Results
-------------	---------

Det Norske Veritas Type Approval – K-1629 Impact Test – DIN 30671 Impact Test – ASTM D2794 Abrasion Test – Taber – BS 2782 Method 370 Norsok M-501 System 7 Submerged

Exposure	Fumes	Splashes & Spills
Acids	Good	Fair
Alkalies	Excellent	Very Good
Solvents	Good	Fair
Water	Excellent	Excellent

TYPICAL CHEMICAL RESISTANCE

Exposure	Fumes	Splashes & Spills
Acids	Excellent	Very Good
Alkalies	Excellent	Very Good
Salt	Excellent	Excellent
Solvents	Very Good	Fair
Water	Excellent	Excellent

MIXING & THINNING

Mixing | Power mix separately, then combine and power mix. DO NOT MIX PARTIAL KITS.

Thinning | Up to 25% with Thinner #10

Ratio | 4:1 Ratio (A to B) by Volume

Pot Life | 6 Hours at 75°F and less at higher temperatures.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

Airless Spray | Pump Ratio: 30:1 (min.)*
Volume Output: 2.5 gpm min.
Material Hose: 3/8" I.D. min.
Tip Size: .023-.027"

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Output Pressure: 2100-2400 psi
Filter Size: 60 mesh
*PTFE packings are recommended and available from the pump manufacturer.

Brush & Roller (General) | For small areas only. Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding.

Brush | Use a good quality decorator's brush.

Roller | Use a medium-nap synthetic roller.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	40°F (4°C)	40°F (4°C)	40°F (4°C)	0%
Maximum	95°F (35°C)	125°F (52°C)	100°F (38°C)	85%

Industry standards are for substrate temperatures to be 5°F above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel. Special application techniques may be required above or below normal application conditions.

CURING SCHEDULE

Surface Temp.	Dry to Handle	Final Cure General	Maximum Dry to Recoat for Immersion
40°F (4°C)	24 Hours	18 Days	20 Days
50°F (10°C)	14 Hours	14 Days	20 Days
70°F (21°C)	8 Hours	6 Days	20 Days
85°F (29°C)	6 Hours	4 Days	20 Days

These times are based on a 6-8 mil dry film thickness. Higher film thicknesses, insufficient ventilation, or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure.

CLEANUP & SAFETY

Cleanup | Use Thinner #2. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety | Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.

Ventilation | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines.

Carbomastic® 18 NT

PRODUCT DATA SHEET



PACKAGING, HANDLING & STORAGE

Shelf Life	24 months at 40°F-110°F
	*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Storage Temperature & Humidity	40°F-110°F (5°-45°C) 0-100% Relative Humidity
Storage	Store Indoors.

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.